Coherent Charge Fluctuation Spectroscopy: A New Tool to Investigate the Pairing Wave Function

J. Lorenzana

ISC-CNR, Sapienza, University of Rome

B. Mansart, A. Mann, A. Odeh, M. Scarongella, M. Chergui, F. Carbone

EPFL, Lausanne

Istituto dei Sistemi Complessi

Consiglio Nazionale delle Ricerche

Raman Scattering

$$\mathbf{E} = \mathbf{E}_0 e^{-i\omega_L t}$$



$$\mathbf{P} = \boldsymbol{\chi}.\mathbf{E} \qquad \varepsilon = 1 - 4\pi\boldsymbol{\chi}$$

$$\boldsymbol{\chi} = \frac{\sigma}{i\omega}$$

$$\boldsymbol{\chi} = \boldsymbol{\chi}_0 + \frac{\partial \boldsymbol{\chi}}{\partial \xi}\xi + \frac{\partial \boldsymbol{\chi}}{\partial \xi^*}\xi^*$$

Raman tensor

$$\mathbf{P} = \left(\boldsymbol{\chi}_0 e^{-i\omega_L t} + \frac{\partial \boldsymbol{\chi}}{\partial \xi}\xi e^{-i(\omega_L + \omega_{ph})t} + \frac{\partial \boldsymbol{\chi}}{\partial \xi^*}\xi^* e^{-i(\omega_L - \omega_{ph})t} \right)\mathbf{E}_0$$

Raman Scattering

$$H = H_{ph} - \frac{1}{2}\mathbf{E}(t).\frac{\partial\chi(\omega_L)}{\partial\xi}.\mathbf{E}(t)\hat{\xi}$$

$$\hat{\boldsymbol{\rho}} = \frac{\partial\boldsymbol{\chi}}{\partial\xi}(\omega_L)\hat{\xi}$$

$$\frac{d\sigma}{d\Omega d\omega} = \frac{\omega_s^4 V^2}{(4\pi)^2 c^4}\sum_{\nu}|\langle 0|\hat{e}_s.\hat{\rho}.\hat{e}_l|\nu\rangle|^2\delta(\omega-\omega_\nu)$$

Sugai PRB '89



FIG. 10. Incident wavelength dependence of the Raman spectra in La_2CuO_4 at 30 K.

Coherent Excitation of phonons by Impulsive Stimulated Raman Scattering

Merlin ssc 1997, Stevens, Kuhl, Merlin PRB 2002

$$H = H_{ph} - \frac{1}{2}\mathbf{E}(t).\frac{\partial\chi(\omega_L)}{\partial\xi}.\mathbf{E}(t)\hat{\xi} = H_{ph} - F(t)\hat{\xi}$$

$$H_{ph} = \frac{1}{2}\Pi^2 + \frac{1}{2}\omega_{ph}^2\xi^2$$

$$\ddot{\xi} + \omega_{ph}^2\xi = F(t)$$

$$\xi(t) = \int_{-\infty}^{t} dt' \frac{\sin[\omega_{ph}(t-t')]}{\omega_{ph}} F(t)$$

pump || [100] 1.55eV
probe || [001] broad band
La2-x SrxCuO4 x=0.15





Okamoto (Yesterday), Demsar (this morning)

Detection of Excitations

$$\xi(t) = \int_{-\infty}^{t} dt' \frac{\sin[\omega_{ph}(t-t')]}{\omega_{ph}} F(t)$$

$$\boldsymbol{\varepsilon} = 1 - 4\pi\boldsymbol{\chi}$$

$$\delta\epsilon_{\mu\nu}(t) = -4\pi \frac{d\chi_{\mu\nu}}{d\xi}\xi(t)$$

pump || [100]
probe || [001]





Swiss Knife Matrix Element

$$\frac{d\chi_{\mu\nu}}{d\xi} =$$



Spontaneous Raman scattering

Coherent generation of excitations

Coherent control of excitations

Detection of excitations

Real time Raman vs Frequency Domain

- Phase sensitive information
- Raman profile in one shot
- Coherent control of excitations





A new coherent excitation







pump ∥ [110]
probe ∥ [110]

x=0.15

Coherent generation of excitations

Phonons

$$H = H_{ph} - \frac{1}{2}\mathbf{E}(t).\frac{\partial\chi(\omega_L)}{\partial\xi}.\mathbf{E}(t)\hat{\xi}$$

$$= H_{ph} - F(t)\hat{\xi}$$

$$\xi(t) = \int_{-\infty}^{t} dt' \frac{\sin[\omega_{ph}(t-t')]}{\omega_{ph}} F(t)$$

Charge Fluctuations

$$H = H_{BCS} - \frac{1}{2}\mathbf{E}(t).\frac{\partial\chi(\omega_L)}{\partial N_X}.\mathbf{E}(t)\hat{N}_X$$

$$= H_{BCS} + v_X(t)\hat{N}_X$$

$$\delta N_X(t) =$$

$$-i\int_{-\infty}^{t} dt' \langle[\hat{N}_X(t), \hat{N}_X(t')]\rangle v_X(t)$$

Magnetism and Superconductivity

Anderson Phys. Rev 1958

$$H_{BCS} = \sum_k \xi_k c^\dagger_{k\sigma} c_{k\sigma} - \sum_k (\Delta^*_k c^\dagger_{-k\downarrow} c^\dagger_{k\uparrow} + h.c.)$$

$$\sigma^x_{\mathbf{k}} = (c_{\mathbf{k}\uparrow} c_{-\mathbf{k}\downarrow} + h.c.),\ i\sigma^y_{\mathbf{k}} = (c_{\mathbf{k}\uparrow} c_{-\mathbf{k}\downarrow} - h.c.),\ \sigma^z_{\mathbf{k}} = 1 - n_{\mathbf{k}\uparrow} - n_{-\mathbf{k}\downarrow}$$

$$|BCS\rangle = \prod_k \left(u_k + v_k c^+_{-k\downarrow} c^+_{k\uparrow}\right)|0\rangle$$



Magnetism and Superconductivity

Anderson Phys. Rev 1958

$$H_{BCS} = \sum_k \xi_k c^\dagger_{k\sigma} c_{k\sigma} - \sum_k (\Delta^*_k c^\dagger_{-k\downarrow} c^\dagger_{k\uparrow} + h.c.)$$

$$H_{BCS} = -\sum_{\mathbf{k}} [\mathbf{b}^0_{\mathbf{k}} + \delta \mathbf{b}_{\mathbf{k}}(t)].\boldsymbol{\sigma}_{\mathbf{k}}.$$

$$\mathbf{b}^0_{\mathbf{k}} = (\Delta_{\mathbf{k}}, 0, \xi_{\mathbf{k}})$$

$$\delta \mathbf{b}_{\mathbf{k}}(t) = (0, 0, v^X_{\mathbf{k}}(t))$$



$$\hbar \frac{\partial \boldsymbol{\sigma}_{\mathbf{k}}}{\partial t} = -2[\mathbf{b}^0_{\mathbf{k}} + \delta \mathbf{b}_{\mathbf{k}}(t)] \times \boldsymbol{\sigma}_{\mathbf{k}}.$$ NMR like !



Larmor at Ef $\omega_k = 2\Delta_k$

NMR in Charge Space



NMR in Charge Space



T_2*

Coherent Charge Fluctuation Spectroscopy

$$\delta\epsilon(\omega,t) = -4\pi \sum_X \frac{\partial\chi}{\partial N_X}(\omega)\langle N_X\rangle(t)$$



Very specific!







Glue Debate

Anderson, Scalapino, Science 2007

Scalapino: Numerics support a retarded interaction scenario.
Paramagnons are the glue.

Anderson: RVB is the true. Do not search for phonons, magnons, etc.
There is no need to be a glue-sniffer.



~20% of the attraction from coupling to high energy states

Maier, Poilblanc, D. J. Scalapino, PRL 2008

B1g Symmetry and Fluency Dependence







A1g+B1g pump ∥ [100] probe ∥ [100]
A1g-B1g pump ∥ [100] probe ∥ [010]

Conclusions

- Superconducting charge fluctuations generated and detected by light pulses for the first time.
- Raman profiles carry precious information on the coupling between low energy excitations and high energy excitations.
- Strong analogy with NMR opens the possibility of coherent control of the superconducting wave function.
- Enables Coherent Charge Fluctuation Spectroscopy, a new technique that allows to answer the question: Which excitations are coupled to the superconducting quasiparticles. High specificity like Isotope effect.
- In our system: Excitations at the scale of the Hubbard U are coupled to low energy charge fluctuations? Signature of Mottness in the superconducting wave function.

Polarization Analysis



Raman Scattering: the A_{1g} La Phonon





$$\Delta = \Delta_0 + Ze^2\left(\frac{1}{d_{LaO}} - \frac{1}{d_{LaCu}}\right)$$

el-ph

$$\frac{d\chi}{d\xi} = \frac{d\chi}{d\Delta}\frac{d\Delta}{dz}\frac{dz}{d\xi}$$

$$\frac{d\chi}{d\Delta} \approx -\frac{d\chi}{d\omega}$$



$$\sqrt{M_{La}}\mathbf{u}_{La} = \mathbf{e}_{La}\xi\exp(-i\omega t) + \mathbf{e}^*_{La}\xi^*\exp(i\omega t)$$

Raman profile as a fingerprint of excitations

$$\delta\epsilon_{xx}(\omega,t) = -4\pi\frac{\partial\chi_{xx}}{\partial n_{CT}}(\omega)\delta n_{CT}(t)$$

pump ∥ [110]
probe ∥ [110]
X=0.15









NMR in Charge Space

Carbone_movies2.gif

NMR in Charge Space



High-Tc Cuprates

Correlated Insulator

Fermi Liquid

Left Revolutionaries

Right Conservatives/Reformists



Raman Scattering





Raman Scattering

$$\xi(t) = \xi e^{-i\omega_{ph}t}$$

$$\sqrt{M_i}\mathbf{u}_i = \mathbf{e}_i \xi e^{-i\omega_{ph}t} + \mathbf{e}_i^* \xi^* e^{i\omega_{ph}t}$$



$$\boldsymbol{\alpha} = \frac{e^2}{m}\frac{\mathbf{F}}{\omega_{0f}^2 - \omega^2 - i\omega\gamma}$$

$$\boldsymbol{\alpha} = \boldsymbol{\alpha}_0 + \frac{\partial \boldsymbol{\alpha}}{\partial \xi}\xi e^{-i\omega_{ph}t} + \frac{\partial \boldsymbol{\alpha}}{\partial \xi^*}\xi^* e^{i\omega_{ph}t}$$

$$\mathbf{p} = \boldsymbol{\alpha}.\mathbf{E} \qquad \mathbf{E} = \mathbf{E}_0 e^{-i\omega_L t}$$

$$\mathbf{p} = \left(\boldsymbol{\alpha}_0 e^{-i\omega_L t} + \frac{\partial \boldsymbol{\alpha}}{\partial \xi}\xi e^{-i(\omega_L + \omega_{ph})t} + \frac{\partial \boldsymbol{\alpha}}{\partial \xi^*}\xi^* e^{-i(\omega_L - \omega_{ph})t}\right)\mathbf{E}_0$$

Conventional Superconductors



Conservative/Reformist View



$$V_{\text{tot}}(\mathbf{r},t) = V_{\text{dir}}(\mathbf{r},t) + V_{\text{ind}}(\mathbf{r},t)$$

$$V_{\text{ind}}(\mathbf{r},t) = -\, e\, e'\, g_n^{\,2}\, \chi_n(\boldsymbol{r},\, t) - \boldsymbol{s}\bullet\boldsymbol{s}'\, g_m^{\,2}\, \chi_m(\boldsymbol{r},t)$$

^{3}He: Leggett, RMP 1975

Superconductors: Monthoux, Pines, Lonzarich, Nature 2007

“Left Revolutionary”

PW Anderson

RVB
Scales U and J
Important
No retardation



Raman Scattering

Example: The A1g La Phonon



$$\Delta = \Delta_0 + Ze^2\left(\frac{1}{d_{LaO}} - \frac{1}{d_{LaCu}}\right)$$

$$\sqrt{M_{La}}\mathbf{u}_{La} = \mathbf{e}_{La}\xi\exp(-i\omega t) + \mathbf{e}^*_{La}\xi^*\exp(i\omega t)$$



el-ph

$$\frac{d\chi}{d\xi} = \frac{d\chi}{d\Delta}\frac{d\Delta}{dz}\frac{dz}{d\xi}$$

$$\frac{d\chi}{d\Delta} \approx -\frac{d\chi}{d\omega}$$





Raman in Solids

$$\mathbf{P} = n\mathbf{p} \qquad \boldsymbol{\chi} = n\boldsymbol{\alpha} \qquad \mathbf{P} = \boldsymbol{\chi}.\mathbf{E} \qquad \boldsymbol{\varepsilon} = 1 - 4\pi\boldsymbol{\chi} \qquad \boldsymbol{\chi} = \frac{\boldsymbol{\sigma}}{i\omega}$$

$$\boldsymbol{\chi} = \boldsymbol{\chi}_0 + \frac{\partial \boldsymbol{\chi}}{\partial \xi}\xi e^{-i\omega_{ph}t} + \frac{\partial \boldsymbol{\chi}}{\partial \xi^*}\xi^* e^{i\omega_{ph}t}$$

$$\omega_R = \omega_L - \omega_s$$

$$\frac{d\sigma}{d\Omega d\omega} = \frac{\omega_s^4 V^2}{(4\pi)^2 c^4} \underbrace{\sum_{\nu} |\langle 0|\hat{e}_s.\hat{\rho}.\hat{e}_l|\nu\rangle|^2 \delta(\omega_R - \omega_\nu)}_{\frac{1}{\pi}\mathrm{Im}\Pi(\omega_R)}$$

$$\hat{\boldsymbol{\rho}} = \frac{\partial \boldsymbol{\chi}}{\partial \xi}(\omega_L)\xi$$

$$\hat{\rho}_{\mu\nu} = \sum_{yX} \frac{\partial \chi_{\mu\nu}}{\partial N_{yX}}(\omega_L)\hat{N}_{yX}$$

$$\Pi(\omega) = i\int_{-\infty}^{t} dt' e^{i\omega t'} \left\langle \left[\hat{e}_L.\hat{\boldsymbol{\rho}}(t).\hat{e}_s, \hat{e}_L.\hat{\boldsymbol{\rho}}(t').\hat{e}_s\right]\right\rangle$$

Cardona, Light Scattering in Solids II

Heavy Fermions





Coherent Excitation of charge fluctuations by Impulsive Stimulated Raman Scattering

$$H_R(t) = -\frac{1}{2}\sum_k \mathbf{E}(t).\chi_{el}^R.\mathbf{E}(t) f_k^X (n_{k\uparrow} + n_{-k\downarrow})$$

$$H_R(t) = \sum_k v_k^X(t)(n_{k\uparrow} + n_{-k\downarrow})$$

$$v_k^X(t) = -\frac{1}{2}\mathbf{E}(t).\chi_{el}^R.\mathbf{E}(t) f_k^X$$



Optical Conductivity and Fluctuations





$$\delta n(\mathbf{r}_i) \propto c \quad \mathbf{r}_i \mathbf{Q} + \theta) \quad \mathbf{Q} = (\pi/2, 0)$$





J.L & G.S., PRL **90**, 066404(2003)

Unconventional Superconductors

$$V_{\text{ind}}(\mathbf{r},t) = -\, e\, e'\, g_n^{\,2}\, \chi_n(\mathbf{r},\, t) - \mathbf{s}\bullet\mathbf{s}'\, g_m^{\,2}\, \chi_m(\mathbf{r},t)$$

Close to instabilities the susceptibility is large at small energies (long times)



Raman Scattering

$$H = H_{ph} - \frac{1}{2}\mathbf{E}(t).\frac{\partial\chi(\omega_L)}{\partial\xi}.\mathbf{E}(t)\hat{\xi} = H_{ph} - F(t)\hat{\xi}$$



$$\frac{d\sigma}{d\Omega d\omega} = \frac{\omega_s^4 V^2}{(4\pi)^2 c^4}\underbrace{\sum_{\nu}|\langle 0|\hat{e}_s.\hat{\rho}.\hat{e}_l|\nu\rangle|^2\delta(\omega_R - \omega_\nu)}_{\frac{1}{\pi}\mathrm{Im}\Pi(\omega_R)}$$

$$\hat{\boldsymbol{\rho}} = \frac{\partial\boldsymbol{\chi}}{\partial\xi}(\omega_L)\xi$$

$$\Pi(\omega) = i\int_{-\infty}^{t} dt' e^{i\omega t'}\langle[\hat{e}_L.\hat{\boldsymbol{\rho}}(t).\hat{e}_s, \hat{e}_L.\hat{\boldsymbol{\rho}}(t').\hat{e}_s]\rangle$$



FIG. 9. Raman spectra of $(La_{1-x}Sr_x)_2CuO_4$ with $x=0.035$ at 30 and 337 K in the (z,z) (solid curves) and (x,z) (dotted curves) polarization configurations.

Sugai PRB '89



FIG. 10. Incident wavelength dependence of the Raman spectra in La_2CuO_4 at 30 K.